

## WPSK-455A

Commercial Grade Polypropylene-Scrim-Kraft (PSK) Facing. It consists of 30u white PP film, closer 3-way fiberglass scrim, 50gsm Kraft paper. Excellent facing and vapor barrier of glasswool blanket / board. Combine with glasswool blanket, it is good at roof and wall insulation of metal building. Very good for air-conditioning ductwork thermal insulation when laminating on glasswool blanket / board.

### Shengli Abrasvie & Adhesive

#### Facing Composition

Facing Composition	Description	Value (English)	Value (Metric)
White Film	Polypropylene	1.2 mil	30 micron
Reinforcing - MD	Fiberglass	4 / inch	16 / 100mm
Reinforcing - XD	Fiberglass	4 / inch	16 / 100mm
Adhesive	Glue	-----	-----
Kraft	Natural	30 lbs / 3000 ft2	50gsm

#### Typical Physical Properties

Physical Properties	Test Method	Value (English)	Value (Metric)
Basis Weight	Scale	17.4 lbs / 1000 ft2	85 gsm
Permeance (WVTR)	ASTM E96, Procedure A	0.02 perm	1.15 ng/N.s
Tensile Strength - MD	ASTM D828	36.4 lbs/in	160 N/25mm
Tensile Strength - XD	ASTM D828	23.9 lbs/in	105 N/25mm
Burst Strength	ASTM D774	94.3 psi	65 N/cm2
Low Temperature Resistance	ASTM D1790 4 hrs @ -40 °F (- 40 °C)	Remains Flexible No Delamination	Remains No Delamination
High Temperature Resistance	ASTM D1790 4 hrs @ +240 °F (+116 °C)	Remains Flexible No Delamination	Remains No Delamination
Dimensional Stability	ASTM D1204 @ 150F	Less than 0.5%	Less than 0.5%
Light Reflectance	ASTM C523	85%	85%

